

HP20NS



Description: Homopolymer
Features: Nucleated and antistat, easy moldability, fast cycle times, improved stiffness, low static charge
Applications: Injection Molding: Consumer products, housewares, rigid packaging
Regulatory: FDA-21 CFR 177.1520 (c)

Typical Properties	Values	ASTM Test Method
Melt Flow	20 g/10 min	D1238
Tensile		D638
Yield Strength	5500 psi	
Yield Elongation	6.0%	
Elongation at Break	20.0%	
Flexural Modulus Tangent	255000 psi	D790A
Deflection Temperature @ 66 psi	240°F	D648

The information contained herein is based on reliable testing methods and is believed to be accurate. However, Thornton and Company, Inc. does not create and expressly disclaims all warranties, express or implied, including warranties of merchantability or fitness for a particular purpose. It is the exclusive responsibility of the user to make its own assessment and determination of the safety and suitability of the product for their specific intended use(s).

453 North Main Street, Suite 316
Southington, CT 06489
Telephone: (860) 628-6771