

I100G



Description: Impact Copolymer
Features: High flow, good stiffness, good colorability, good impact resistance,
Applications: Extrusion compounding
Regulatory: FDA-21 CFR 177.1520 (c)

Typical Properties	Values	ASTM Test Method
Melt Flow	100 g/10 min	D1238
Density	0.90 g/cm ³	D1505
Tensile		D638
Yield Strength	3800 psi	
Yield Elongation	5.0%	
Flexural Modulus	190000 psi	D790
Notched Izod Impact Strength @ 73°F	1.0 ft-lb./in.	D256A
Deflection Temperature @ 66 psi	212°F	D648

The information contained herein is based on reliable testing methods and is believed to be accurate. However, Thornton and Company, Inc. does not create and expressly disclaims all warranties, express or implied, including warranties of merchantability or fitness for a particular purpose. It is the exclusive responsibility of the user to make its own assessment and determination of the safety and suitability of the product for their specific intended use(s).

453 North Main Street, Suite 316
Southington, CT 06489
Telephone: (860) 628-6771